



200 Tillessen Blvd, Ridgeway, SC USA 29130

Style 1067

Generic Description: 0.71 oz. per square yard (24.4 g/m²) plain weave fiberglass fabric

Product Description: IPC Style 1067

Property	Description	Value and Tolerance		Test Method
		English	Metric	
Weave Type	Plain			ASTM D 579
Finish	Greige			
Warp count		70 +/- 2 epi	27.6 +/- 0.8 epc	ASTM D 3775
Fill count		70 +/- 2 ppi	27.6 +/- 0.8 ppc	ASTM D 3775
Warp Yarn Type		ECD 900 1/0	EC 5 5.5 1X0	ASTM D 579
Fill Yarn Type		ECD 900 1/0	EC 5 5.5 1x0	ASTM D 579
Selvedge	Feathered	0.375 +/- 0.250	9.53 +/- 6.35	Visual
Roll Splice	Lapped Splice	Max - 2 splices / roll Minimum 50 LY between splices	Max - 2 splices / roll Minimum 45.7 LM between splices	Roll Splice
Color	White			Visual

Physical Properties:

Property	Description	Value and Tolerance		Test Method
		English	Metric	
LOI		< 4%	< 4%	ASTM D 4963
Greige Weight		0.91 OSY +/- 10%	30.7 g/m ² +/- 10%	ASTM D 3776
Thickness		0.0014 +/- 0.0005 in	0.0350 +/- 0.013 mm	ASTM D 1777
Warp Breaking strength		25 lb/in. minimum	43.8 N/cm minimum	ASTM D 5035
Weft Breaking Strength		20 lb/in. minimum	35.0 N/cm minimum	ASTM D 5035

Packaging and Labeling

Core ID and thickness	3 in. ID, 4 in. OD. standard core
Shipping Requirements	Best way